

# 100 Cr 6

# 1.2067

BL3

L3

## Richtanalyse / chemical analysis in %

C	Si	Mn	P	S	Cr	Mo	Ni	V	W
0,95	0,15	0,25			1,45	-	-	-	-
-	-	-	<	<	-				
1,10	0,35	0,45	0,025	0,020	1,65	-	-	-	-


## Wärmebehandlung / heattreatment advice

Härteempfehlung  
recommendation of hardening

820-860°C / 1510-1580°F

Abschreckmittel  
quenching medium

Öl / oil



## Anwendungsbeispiele / examples of use

- Hobelmesser / planer knives
- Aufschnittmesser / food processing knives, slicers
- Papierkreismesser / circular paper knives
- Maschinenmesser / machine knives

und andere Industriemesser / and other industrial knives