

110 WCrV 5

1.2519

Richtanalyse / chemical analysis in %

C	Si	Mn	P	S	Cr	Mo	Ni	V	W
1,05	0,20	0,20			1,10	-	-	-	1,20
-	-	-	<	<	-				-
1,15	0,30	0,40	0,025	0,020	1,30	-	-	-	1,40


Wärmebehandlung / heattreatment advice

Härteempfehlung
recommendation of hardening

800-830°C / 1475-1525°F

Abschreckmittel
quenching medium

Öl / oil



Anwendungsbeispiele / examples of use

- Ledermesser / leather cutting knives
- Gummimaschinenmesser / rubber cutting machine knives
- Plastik- und Folienmesser / plastic- and foil cutting knives
- Maschinenmesser / machine knives

und andere Industriemesser / and other industrial knives